

EI 收录期刊
中文核心期刊
中国科技核心期刊

ISSN 1007—7812
CODEN HUXUFP

火炸药学报

HUOZHAYAO XUEBAO

CHINESE JOURNAL OF
EXPLOSIVES & PROPELLANTS

(Chin J Explos Propellants)

Vol.45 No.1

2022

中国兵工学会

ISSN 1007-7812



火炸药学报

第四十五卷

二〇二二年
第一期(总第三二期)

本刊系《中文核心期刊要目总览》(2020 年版)、国务院《学位与研究生教育重要期刊》、科技部《中国科技论文统计源期刊》(中国科技核心期刊)、中国科学院《中国科学引文数据库》及中国科协《中国学术期刊文摘(英文版)》、美国《化学文摘》(CA)、Scopus 数据库、Ei Compendex 数据库、俄罗斯《文摘杂志》(AJ)、日本 JST China 数据库、美国《乌利希期刊指南(网络版)》(Ulrichsw eb)数据库收录源刊。

刊名题写:张爱萍

目 次

金石观点

议论火炸药数字化制造 肖忠良(i)

综 述

墨水直写增材制造技术及其在含能材料领域的研究进展 姜一帆,赵凤起,李 辉,张 明,蒋周峰,侯晓婷,张建侃,李 娜,戴亚堂(1)

1,1'-二羟基-5,5'-联四唑二羟胺盐在火炸药中的应用研究进展 张 坤,王 健,王晓峰,冯晓军(20)

单质含能材料

5,5'-二硝基-3,3'-联(1,2,4-三唑)草酰肼双阳离子盐的合成、表征与性能预估 周飞飞,侯天骄,罗 军(30)

High Energy Density Materials based on N_4 Molecules: Synthesis Routes from First-principles Calculations MAO Yu-ting, SUN Chu-li, DU Hui-fang, GUO Wei(36)

超重力辅助溶剂-反溶剂重结晶法制备亚微米级 RDX 曹少博,周林裕,张亮亮,陈建峰(46)

富勒烯对甲基苯胺衍生物的合成及其对硝化棉安定性的影响 熊 杰,金致远,余雪梅,金 波,彭汝芳(53)

含能复合物

静电喷雾法制备 TKX-50/Al/GAP 含能微单元及其性能研究 叶宝云,冯宸赫,安崇伟,王晶禹,赵凤起,赵嘉静(60)

GAP/PET 嵌段型热塑性聚氨酯弹性体的低温力学性能 徐明辉,杨伟涛,卢先明,莫洪昌,葛忠学(67)

混合炸药及毁伤

线内非同步起爆对战斗部毁伤效能的影响 张树凯,王科伟,谢佳良,李晓刚,张浩宇,程 立(73)

HTPB/增塑剂表面自由能研究 牛国涛,南 海,牛余雷(81)

DFTNAN/B 的热分解行为及相容性 朱 煜,王建华,刘玉存,荆苏明,翟思源,温 旭(85)

振动作用对现场混装乳化炸药稳定性的影响 魏 国,刘 锋,吴攀宇,王锡东(90)

推进剂及应用

CL-20/CMDB 推进剂的宽温力学临界转变特性 胡义文,王江宁,张 军,袁志锋,陈俊波,陈太俊,宋秀铎,裴江峰,耿超辉(97)

EPDM 包覆层注射成型模拟及工艺参数研究 刘奔奔,张 慧,李军强,陈国辉,杨士山,彭 炯,何吉宇,李向梅,杨荣杰(103)

发射药及装药

典型高能硝胺发射药的摩擦静电起电特性 石先锐,许灿啟,贾永杰,李小东(109)

基于人工神经网络算法的发射药钝感剂浓度分布快速预测技术 苟永亮,刘 波,李梓超,魏 伦,马方生,姚月娟,于慧芳,李 强(115)

火炸药安全

氧化石墨烯对 RDX/PMMA 安全性能及力学性能影响 侯聪花,张 鑫,马静静,张诗敏,吴 楠,李泽睿,杜宇星(120)

BFFO 的热安全性和凝固特性 巨荣辉,罗一鸣,王 浩,蒋秋黎,张蒙蒙,杨 斐,翟连杰,王锡杰(126)

* * * * *

Contents

Reviews

- Direct Ink Writing Technology for Additive Manufacturing and Its Research Progress in Energetic Materials JIANG Yi-fan,ZHAO Feng-qi,LI Hui, et al(1)
- Application and Research Progress of Dihydroxylammonium 5,5'-bistetrazole-1,1'-diolate (TKX-50) in Explosives & Propellants ZHANG Kun,WANG Jian,WANG Xiao-feng, et al(20)

Energetic Elemental Materials

- Synthesis,Characterization and Performance Prediction of Oxalohydrazidinium 5,5'-dinitro-3,3'-bi(1,2,4-triazolate) ZHOU Fei-fei,HOU Tian-jiao,LUO Jun(30)
- High Energy Density Materials based on N₄ Molecules ; Synthesis Routes from First-principles Calculations MAO Yu-ting,SUN Chu-li,DU Hui-fang,et al(36)
- Preparation of Submicron RDX Particles by High-gravity Assisted Solvent-Antisolvent Recrystallization Method CAO Shao-bo,ZHOU Lin-yu,ZHANG Liang-liang, et al(46)
- Synthesis of Fullerene p-Methylaniline Derivative and Its Effect on the Stability of Nitrocellulose XIONG Jie,JIN Zhi-yuan,YU Xue-mei, et al(53)

Energetic Composites

- Preparation of TKX-50/Al/GAP Energetic Micro-units by Electrostatic Spraying Method and Its Performance YE Bao-yun,FENG Chen-he,AN Chong-wei, et al(60)
- Cryogenic Mechanical Properties of GAP/PET Block Thermoplastic Elastomers XU Ming-hui,YANG Wei-tao,LU Xian-ming, et al(67)

Mixed Explosives and Damage

- Effect of In-line Asynchronous Initiation on Warhead Damage Efficiency ZHANG Shu-kai,WANG Ke-wei,XIE Jia-liang, et al(73)
- Study on the Surface Free Energy of HTPB/Plasticizers NIU Guo-tao,NAN Hai,NIU Yu-lei(81)
- Thermal Decomposition Behavior and Compatibility of DFTNAN/B ZHU Yu,WANG Jian-hua,LIU Yu-cun, et al(85)
- Influence of Vibration on the Stability of On-site Mixed Emulsion Explosive WEI Guo,LIU Feng,WU Pan-yu, et al(90)

Propellants and Application

- Mechanical Critical Transition Characteristics of CL-20/CMDB Propellants over a Wide Range of Temperature HU Yi-wen,WANG Jiang-ning,ZAHNG Jun, et al(97)
- Research on Injection Molding Simulation and Process Parameters of EPDM Coating LIU Ben-ben,ZHANG Hui,LI Jun-qiang, et al(103)


Gun Propellants and Charge

- Frictional Static Electricity Characteristics of Typical High Energy Nitramine Gun Propellant SHI Xian-rui,XU Can-qi,JIA Yong-jie, et al(109)
- Prediction of Desensitizer Concentration Distribution in Gun Propellant Based on Artificial Neural Network Algorithm GOU Yong-liang,LIU Bo,LI Zi-chao, et al(115)

Safety of Explosive

- Effect of Graphene Oxide on Safety Performance and Mechanical Properties of RDX/PMMA HOU Cong-hua,ZHANG Xin,MA Jing-jing, et al(120)
- Thermal Safety and Solidification Characteristics of BFFO JU Rong-hui,LUO Yi-ming,WANG Hao, et al(126)

Direct Ink Writing Technology for Additive Manufacturing and Its Research Progress in Energetic Materials




The basic characteristics of direct ink writing (DIW) technology and its application in energetic materials are systematically introduced. Recent research progresses for DIW technology used in metastable intermolecular composites (thermite, aluminum-fluorine polymer), propellants and explosives grains with complex structure, and explosive agents are mainly summarized. Moreover, the main challenges and the opportunities are also analyzed, which provide a guidance for the development and application of DIW in energetic materials.

JIANG Yi-fan, ZHAO Feng-qj, LI Hui, ZHANG Ming, JIANG Zhou-feng, HOU Xiao-ting, ZHANG Jian-kan, LI Na, DAI Ya-tang

Chinese Journal of Explosives & Propellants, 2022, 45(1): 1-19.

Application and Research Progress of Dihydroxylammonium 5,5'-bistetrazole-1,1'-diolate (TKX-50) in Explosives & Propellants




The current research status of dihydroxylammonium 5,5'-bistetrazole-1,1'-diolate (TKX-50) compound on its performance improvement, synthesis and preparation, crystal properties, mechanical properties compatibility, energy, and safety are summarized. The application advantages and existing problems of TKX-50 are pointed out, and the future development direction and research focus are prospected.

ZHANG Kun, WANG Jian, WANG Xiao-feng, FENG Xiao-jun

Chinese Journal of Explosives & Propellants, 2022, 45(1): 20-29.

Synthesis , Characterization and Performance Prediction of Oxalohydrazidinium 5,5'-dinitro-3,3'-bi(1,2,4-triazolate)





The gemini energetic ionic salt oxalohydrazidinium 5,5'-dinitro-3,3'-bi(1,2,4-triazolate) was synthesized by the acid-base neutralization reaction of 5,5'-dinitro-3,3'-bi(1,2,4-triazole) with oxalyl hydrazide. The structure of the compound was characterized by single crystal X-ray diffraction, infrared spectroscopy, and nuclear magnetic resonance. The detonation performances and stability were also calculated and tested.

ZHOU Fei-fei , HOU Tian-jiao , LUO Jun

Chinese Journal of Explosives & Propellants ,2022 ,45(1) : 30-35 .

High Energy Density Materials based on N₄ Molecules : Synthesis Routes from First-principles Calculations

N₄ molecule on metal surface




N₄ molecule in crystals

Through coordination bond between N₄ and metal atoms , polymerized N₄ can be synthesized at high pressure and stabilized at low temperature conditions .

MAO Yu-ting , SUN Chu-li , DU Hui-fang , GUO Wei

Chinese Journal of Explosives & Propellants ,2022 ,45(1) : 36-45 .


Preparation of Submicron RDX Particles by High-gravity Assisted Solvent-Antisolvent Recrystallization Method



Submicron RDX was prepared through a high-gravity assisted solvent-antisolvent recrystallization method by using acetone-water medium as solvent-antisolvent system, and the polyvinylpyrrolidone (PVP) as surfactant. The effects of RDX solution concentration, PVP concentration and rotating speed of high-gravity reactor on the morphology and size of RDX were studied, and the optimal process conditions were obtained. The morphology, crystal structure and molecular structure of RDX were characterized by SEM, XRD and FT-IR, and the thermal decomposition process of RDX was studied by DSC.

CAO Shao-bo, ZHOU Lin-yu, ZHANG Liang-liang, CHEN Jian-feng
Chinese Journal of Explosives & Propellants, 2022, 45(1): 46-52.


Synthesis of Fullerene p-Methylaniline Derivative and Its Effect on the Stability of Nitrocellulose



Fullerene p-methylaniline derivative $C_{60}(NC_6H_4CH_3)_n$ was synthesized via a two-step reaction by using fullerene, Br_2 , $C_{60}Br_8$ and p-toluidine as raw materials. The structure of fullerene p-methylaniline derivative was characterized by nuclear magnetic resonance (^{13}C NMR), mass spectrometry (MS), X-ray photoelectron spectroscopy (XPS), Fourier transform infrared spectroscopy (FT-IR) and ultraviolet-visible spectrophotometer (UV-Vis). Thermal analysis methods such as differential thermal analysis (DTA), vacuum stability test (VST), thermogravimetric analysis (TGA) and methyl violet test were used to study the interactive mechanism between fullerene p-methylaniline derivative and nitrocellulose.

XIONG Jie, JIN Zhi-yuan, YU Xue-mei, JIN Bo, PENG Ru-fang
Chinese Journal of Explosives & Propellants, 2022, 45(1): 53-59.


Preparation of TKX-50/Al/GAP Energetic Micro-units by Electrostatic Spraying Method and Its Performance



TKX-50/Al/GAP composite microspheres were prepared by electrostatic spraying. The morphology, structure and thermal decomposition properties of the microspheres were studied by SEM, XRD, FT-IR and DSC. The mechanical sensitivities of the microspheres were also tested.

YE Bao-yun, FENG Chen-he, AN Chong-wei, WANG Jing-yu, ZHAO Feng-qi, ZHAO Jia-jing
Chinese Journal of Explosives & Propellants, 2022, 45(1): 60-66.

Cryogenic Mechanical Properties of GAP/PET Block Thermo-plastic Elastomers




The GAP/PET block thermo-plastic elastomers were synthesized using GAP and PET as soft segments, and TDI extended BDO as hard segments to enhance their cryogenic mechanical properties. The thermo-plastic elastomers have a low T_g of -37.7°C and exhibit ductile rupture under the low temperature of -40°C .

XU Ming-hui, YANG Wei-tao, LU Xian-ming, MO Hong-chang, GE Zhong-xue

Chinese Journal of Explosives & Propellants, 2022, 45(1): 67-72.

Effect of In-line Asynchronous Initiation on Warhead Damage Efficiency




Four kinds of in-line asynchronous initiation schemes are proposed based on the sequential initiation mode. By LS-DYNA simulation and solving the fragment exterior ballistic equation, the effects of the in-line initiation sequence, delay and the number of initiation lines on the damage efficiency of military vehicles are studied.

ZHANG Shu-kai, WANG Ke-wei, XIE Jia-liang, LI Xiao-gang, ZHANG Hao-yu, CHENG Li

Chinese Journal of Explosives & Propellants, 2022, 45(1): 73-84.

Study on the Surface Free Energy of HTPB/Plasticizers




The effect of the volume ratio of HTPB with plasticizers, the type of plasticizers, the type of plasticizers and temperature on the surface free energy of HTPB/plasticizer was analyzed. The surface free energy of HTPB bonding system was measured by surface energy measuring apparatus.

NIU Guo-tao, NAN Hai, NIU Yu-lei

Chinese Journal of Explosives & Propellants, 2022, 45(1): 81-84.


Thermal Decomposition Behavior and Compatibility of DFT-NAN/B



The thermal decomposition behavior of 3,5-difluoro-2,4,6-trinitroanisole (DFTNAN) and micro-sized boron powder mixture was studied by differential scanning calorimetry (DSC) and thermogravimetric analysis (TGA). With the increase of the heating rate, the reaction between DFTNAN and boron powder is more intense, which is more helpful to remove the oxides on the surface of boron particles.

ZHU Yu, WANG Jian-hua, LIU Yu-cun, JING Su-ming, ZHAI Si-yuan, WEN Xu
Chinese Journal of Explosives & Propellants, 2022, 45(1): 85-89.


Influence of Vibration on the Stability of On-site Mixed Emulsion Explosive



The average particle size, viscosity, crystallinity and conductivity of emulsion matrix were measured by laser particle size analyzer, digital viscometer, titration and conductivity method before and after vibration test.

WEI Guo, LIU Feng, WU Pan-yu, WANG Xi-dong
Chinese Journal of Explosives & Propellants, 2022, 45(1): 90-96.


Mechanical Critical Transition Characteristics of CL-20/CM-DB Propellants over a Wide Range of Temperature



To investigate the mechanical characteristic over a wide range of temperature, the mechanical performance of CL-20/composite modified double base propellant (CL-20/CMDB) was investigated by tensile test and dynamic mechanical analyzer. The mechanical critical transition characteristics at high and low temperatures were studied by thermal deformation test and impact loading test, respectively.

HU Yi-wen, WANG Jiang-ning, ZHANG Jun, YUAN Zhi-feng, CHEN Jun-bo, CHEN Tai-jun, SONG Xiu-duo, PEI Jiang-feng, GENG Chao-hui
Chinese Journal of Explosives & Propellants, 2022, 45(1): 97-102.


Research on Injection Molding Simulation and Process Parameters of EPDM Coating



To improve the development efficiency of ethylene propylene diene monomer (EPDM) rubber coating injection molding process, the flow law of EPDM was studied by combination of numerical simulation and experimental verification and appropriate process parameters were optimized. The rheological properties of EPDM were modeled using the Carreau mode, which was introduced into Moldflow software to simulate the injection molding process of EPDM coating.

LIU Ben-ben, ZHANG Hui, LI Jun-qiang, CHEN Guo-hui, YANG Shi-shan, PENG Jiong, HE Ji-yu, LI Xiang-mei, YANG Rong-jie
Chinese Journal of Explosives & Propellants, 2022, 45(1): 103-108.

Frictional Static Electricity Characteristics of Typical High Energy Nitramine Gun Propellant




The flume method was adopted to simulate the electrostatic electrification by friction of high-energy nitramine gun propellant in the process of manufacture and application, and a Faraday cylinder was used to measure the frictional electrostatic charge. The influence of the flume length, contact medium, humidity, morphology and propellant formulation on the electrostatic accumulation characteristics of the propellants were systematically studied.

SHI Xian-rui, XU Can-qí, JIA Yong-jie, LI Xiao-dong

Chinese Journal of Explosives & Propellants, 2022, 45(1): 109-114.

Prediction of Desensitizer Concentration Distribution in Gun Propellant Based on Artificial Neural Network Algorithm




GOU Yong-liang, LIU Bo, LI Zi-chao, WEI Lun, MA Fang-sheng, YAO Yue-juan, YU Hui-fang, LI Qiang

Chinese Journal of Explosives & Propellants, 2022, 45(1): 115-119.

A method for quickly predicting the concentration distribution of desensitizer in 5/7 modified single-base gun propellant was proposed, and a simple neural network model based on artificial neural network algorithm was established, and the experimental data of desensitizer concentration profile of 5/7 modified single-base propellant was used to train the model.

Effect of Graphene Oxide on Safety Performance and Mechanical Properties of RDX/PMMA




HOU Cong-hua, ZHANG Xin, MA Jing-jing, ZHANG Shi-min, WU Nan, LI Ze-rui, DU Yu-xing

Chinese Journal of Explosives & Propellants, 2022, 45(1): 120-125.

RDX/PMMA/GO particles were prepared by emulsion polymerization method, and compared with those of RDX/PMMA prepared by the same method.

Thermal Safety and Solidification Characteristics of BFFO



JU Rong-hui, LUO Yi-ming, WANG Hao, JIANG Qiu-li, ZHANG Meng-meng, YANG Fei, ZHAI Lian-jie, WANG Xi-jie

Chinese Journal of Explosives & Propellants, 2022, 45(1): 126-132.

The thermal safety of BFFO was studied by DSC test and long-term constant temperature test, and the solidification properties were studied by X-ray transmission imaging, SEM morphology analysis and DSC controlled solidification test, which were also compared with 3, 4-bis (3-nitrofurazan-4-yl) furoxan (DNTF).